

# Thermal conductivity of materials and measuring system at cryogenic temperature

B. Li, B. M. Wu, D. S. Yang, W. H. Zheng, L. Z. Cao

Structural Research Lab., Department of Physics,  
University of Science and Technology of China, Hefei, 230026, P.R. China

A measuring system, including the measuring setup and corresponding software, is developed to perform the measurement of the thermal conductivity of rod samples with millimeter scale in temperature range 4.2-300K. The precisions and applicability are proved by experiments on a number of materials including superconductors, SDW alloys, CMR materials, as well as engineering materials.

## INTRODUCTION

The thermal conductivity of materials is of high importance in both science and engineering fields. There are several mechanisms by which heat can be transmitted through materials and many processes that limit the effectiveness of each mechanism. In a non-metal heat is conducted by means of the thermal vibrations of the atoms. In a simple metal this mode of heat transport makes some contribution, but the observed thermal conductivity is almost entirely due to the electrons. It does not follow that thermal conductivity of the two different materials must be very different in magnitude, as they are in the case of electrical conductivity, but their dependences on temperature and on the imperfections in individual specimens are rather different. In many materials, such as alloys and semiconductors, both transport mechanisms can make comparable contributions to the observed conductivity, and the relative proportions vary with composition and temperature. In superconductors the proportions are different in the normal and superconducting states, so that below the transition temperature they can be changed by an appropriate magnetic field.

In engineering, automotive, aerospace and related industries, thermal conductivity is important design parameters. These industries require access to reliable standards of thermal conductivity to facilitate material development, evaluation and improvement of component design as well as to ensure good quality control of manufactured products. There is also a demand for Certified Reference Materials and Transfer Standards for the calibration of comparative thermal conductivity apparatus that are mainly supplied by US companies. At present the manufacturers supply these apparatus with standards or reference materials that are uncertified and primarily refer to book values of thermal conductivity typical for that material. In the current climate of increasing accreditation of measurement testing facilities auditors are requiring test laboratories to have reference materials whose calibrations are traceable to national standards.

At any rate, it is necessary to measure thermal conductivity exactly. We have developed a thermal conductivity measuring system, including the measuring setup and corresponding control software, to measure the thermal conductivity of rod samples with millimeter scale in temperature range 4.2-300K. The precision and applicability of the system are proved by experiments on kinds of materials including superconductors, SDW alloys, CMR materials, as well as some engineering materials.

## EXPERIMENTAL CONSIDERATIONS

### Method

The method of longitudinal steady thermal flow [1] is used in the measurement. In this simplest steady-state experimental arrangement, heat is supplied at one end of a rod of uniform cross-sectional

area  $A$  at a known rate  $\dot{Q}$  and is removed at the other end. The temperature difference  $\Delta T$  is established with a distance  $L$ . The thermal conductivity is then derived from the relation

$$K = \frac{\dot{Q}}{\Delta T} \cdot \frac{L}{A} \quad (1)$$

### Setup

A schematic view of the experimental chamber setup and sample holder is shown in Figure 1 [2]. Vacuum of the sample chamber was kept  $10^{-4}$  Pa during the measurement. The temperature difference on the sample generated by the gradient heater is monitored directly with a differential thermocouple. The temperature difference on the sample is controlled about 1 K.




Figure 1 Schematic diagram of the experimental setup

### Automation

The real-time read and write are realized by a GPIB interface board and insulated analog output boards respectively, as shown in Figure 2. The temperature instability of the sample is controlled within  $\pm 2mK$  by a PID temperature controller [3]. Corresponding software is developed to collect and process the experimental data.

The Borland C++ Builder 6.0 environment is used to develop the real-time direct digital control software that practices the automation of data collection and process. We pay most attention to the convenience, security and stability of the software as BCB 6.0 provides perfect visualization component libraries (VCL). The measuring system can work properly in temperature range 4.2-300K. The experimental results of different materials are probed continuous and smooth as temperature varies.




Figure 2 Schematic diagram of the real-time data collection and process

## EXPERIMENTAL RESULTS

On this measuring system, we have obtained the thermal conductivity of a number of materials including superconductors [4-10], SDW alloys [11,12], and CMR materials [13, 14], as well as some engineering

materials. The results meet the requirement of numerical analyses and are repeatable. Some typical thermal conductivity temperature dependences are given below.

#### Thermal conductivity of superconductors

The thermal conductivity peak in high  $T_C$  superconductors (HTS) has been validated [4 and its references] under  $T_C$ . Below  $T_C$  superconducting electrons condensing into Cooper pairs carry no heat, the thermal conductivity is thus ensured by normal electrons. Since the normal electron scattering rate in HTSs has been observed to decrease rapidly below  $T_C$ , thermal conductivity should increase under  $T_C$ . As temperature kept decreasing, the number of carriers decreases, that leads to the decreasing of thermal conductivity. The thermal conductivity of high  $T_C$  superconductor  $\text{Hg}_{0.9}\text{Tl}_{0.2}\text{Ba}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  [4] is shown in Figure 3. The thermal conductivity peak under  $T_C$  is remarkable. The thermal conductivity of new superconductor  $\text{MgB}_2$  [6] is shown in Fig. 4. No obvious variation is observed near  $T_C$ .




Figure 3 The thermal conductivity of high  $T_C$  superconductor  $\text{Hg}_{1223}$  and new superconductor  $\text{MgB}_2$

#### Thermal conductivity of CMR materials

The thermal conductivity of CMR material  $\text{La}_{0.7}\text{Ca}_{0.3}\text{Mn}_{0.95}\text{Cr}_{0.05}\text{O}_3$  [12] is shown in Figure 4. A minimum is observed at the Curie temperature ( $T_C$ ), and a phonon-induced peak [1] is observed at about 20K. It is remarkable that the thermal conductivity and electrical conductivity show similar temperature dependence about  $T_C$ . The similarity is more interesting knowing the fact that electron contribution deduced from Wiedemann-Franz law [1] is less 1%. Because of the strong electron-phonon interaction in perovskite structures, electron contributes to the thermal conductivity indirectly as well. The unusual similarity between thermal conductivity and electrical conductivity temperature dependence results from the indirect electron contribution. Above  $T_C$ , electrons are localized around phonons forming polarons. Thus modes of phonon are limited by these localized electrons. Under  $T_C$ , electrons delocalize. As temperature decreasing, more electrons become mobile. Phonons are no more bound to electrons. Thus the thermal conductivity increases with a decreasing temperature.




Figure4 The thermal conductivity of CMR material

#### Thermal conductivity of engineering materials

Both good and poor thermal conductors are demanded in different engineering fields. The thermal conductivity of Ag sheathed Bi-2223 superconducting cable and insulator in superconducting loop are shown in Figure 5. The difference in thermal conductivity is about two orders of magnitudes.

## CONCLUSION

A measuring system, including measuring setup and corresponding software, is developed to measure the thermal conductivity of rod samples with millimeter scale in temperature range 4.2-300K. The precisions and applicability of the system are proved by the measurement performed on kinds of materials.

## ACKNOWLEDGEMENT

This work is supported by the National Nature Science Foundation of China (No.10174070), the Ministry of Science and Technology of China (NKBRSF-G19990646).

## REFERENCES

- 1 R. Berman, *Thermal conduction in Solids*, Clarendon, Oxford, (1976).
- 2 Bai-Mei Wu, Dong-Sheng Yang, Bo Li, Wei-Hua Zheng, Song Sheng, The construct and automatization of thermal conductivity measurement system, *Chinese Journal of Low Temperature* (2003) **25** supp. 248.
- 3 Dong-Sheng Yang, Bai-Mei Wu, Computer based temperature controller in low temperature, *Chinese Journal of Low Temperature*, (1999) **21** 156.
- 4 Dong-Sheng Yang, Bai-Mei Wu, Song Sheng, Ping Zheng, Lie-Zhao Cao, Qin-Lun Xu, Thermal conductivity of superconducting  $\text{Hg}_{0.9}\text{Tl}_{0.2}\text{Ba}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+d}$ , *Chinese Journal of Low Temperature*, (1999) **21** 405.
- 5 Bai-Mei Wu, Dong-Sheng Yang, Ping Zheng, Song Sheng, Zhao-Jia Chen, Qin-Lun Xu, Thermal conductivity of  $\text{Hg}_{0.9}\text{Tl}_{0.2}\text{Ba}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+d}$  in magnetic field, *Acta Physica Sinica*, (2000) **49** 267.
- 6 Dong-Sheng Yang, Bai-Mei Wu, Bo Li, Wei-Hua Zheng, Shi-Yan Li, Rong Fan, Xian-Hui Chen, Lie-Zhao Cao, Thermal Conductivity of Two-Energy-Gap Superconductor  $\text{MgB}_2$ , *Acta Physica Sinica*, (2003) **52** 683.
- 7 Dong-Sheng Yang, Bai-Mei Wu, Bo Li, Wei-Hua Zheng, Shi-Yan Li, Xian-Hui Chen, Lie-Zhao Cao, Anomalous Thermal Conductivity Enhancement in the Mixed State of  $\text{MgB}_2$ , *Acta Physica Sinica*, (2003) **52** 2015.
- 8 Bai-Mei Wu, Bo Li, Dong-Sheng Yang, Wei-Hua Zheng, Shi-Yan Li, Lie-Zhao Cao, Xian-Hui Chen, The Thermal Conductivity in New Superconductor  $\text{MgB}_2$  and  $\text{MgCNi}_3$ , *Acta Physica Sinica*, (2003) **52** 3150.
- 9 Bo Li, Bai-Mei Wu, Dong-Sheng Yang, Wei-Hua Zheng, Hua Jin, Hui-Ping Gao, Thermal Conductivity of Ce Doped Bi-2212, *Chinese Journal of Low Temperature* (2003) **25** supp. 253.
- 10 Dong-Sheng Yang, Bai-Mei Wu, Wei-Hua Zheng, Hong-Shun Yang, Bo Li, Lie-Zhao Cao, Thermal conductivity of excess-oxygen-doped  $\text{La}_2\text{CuO}_4$ , *Chinese Journal of Low Temperature* (2001) **23** 45.
- 11 Bai-Mei Wu, Dong-Sheng Yang, Song Sheng, Wei Liu, Ying-Lei Du, Wei-Ming Xu, The transport properties and internal friction related to the antiferromagnetic transition in  $\text{Cr}_{75}(\text{Fe}_x\text{Mn}_{1-x})_{25}$  alloys, *J. magn. Magn. Mater.*, (1999) **202** 426.
- 12 Bai-Mei Wu, Dong-Sheng Yang, Song Sheng, Wei-Ming Xu, Zhao-Jia Chen, Thermal Conductivity of  $\text{Cr}_{75}\text{Fe}_x\text{Mn}_{25-x}$  ( $x=16,18$ ) Alloys, *Acta Physica Sinica*, (1999) **48** 1147.
- 13 Wei-Hua Zheng, Bai-Mei Wu, Dong-Sheng Yang, Jian-Yang, Li, Xue-Rong, Liu, Bo Li, Ya-Qin Zhou, thermal conductivity and electrical conductivity in  $\text{La}_{1-x}\text{Ca}_x\text{MnO}_3$ , *Chinese Journal of Low Temperature*, (2001) **23** 216.
- 14 Wei-Hua Zheng, Bai-Mei Wu, Bo Li, Dong-Sheng, Yang, Lie-Zhao Cao, Thermal conductivity in  $\text{La}_{0.7}\text{Ca}_{0.3}\text{Mn}_{1-x}\text{Cr}_x\text{O}_3$  at low temperature, *Chinese Journal of Low Temperature*, (2002) **24** 230.




Figure 5 The thermal conductivity of some engineering materials