

Salt saturated water  
from the sea or  
deicing of roads

Pore water in concrete is  
initially saturated with alkalis  
but no chlorides

Initial penetration may be  
by capillary suction during  
wetting and drying cycles

Diffusion transports the  
chloride towards the  
reinforcing steel

Cover layer of concrete structure

